

Eurothane[®] Eurodeck is a thermal insulation board for use in warm flat roofs under mechanically fixed single-ply membrane waterproofing systems

Application(s)

Warm flat roofs under mechanically fixed single-ply membrane waterproofing systems

Board				
Description	Value	Unit	Tolerances	Standard
Dimensions				
Length	2400	mm		
	1200	mm		
	600	mm		
Width	1200	mm		
Thickness	30 - 160	mm	T2	EN 823
Density (core volume weight)	± 30	kg/m³		
Appearance				
Facing	Gas diffusion tight multilayer			
Edge finishing	Straight			

Essential Characteristics				
Description	Standard	EN code	Value	Unit
Thermal conductivity (declared value)				
All thicknesses	EN 13165	λ_{D}	0.022	W/mK
Mechanical properties				
Compressive stress or compressive				
Strength at 10% deformation	EN 826	CS(10/Y)150	≥150	kPa
Fire behaviour				
Reaction to fire (product as such)	EN 13501-1	Euroclass	F	
Hygrometric properties				
Water vapour diffusion resistance factor (Tabulated value)	EN ISO 10456	μ	50-100	

Care has been taken to ensure that the content of this document is as accurate as possible. Please note that technical specifications may vary from country to country. Recticel Insulation does not accept any liability for clerical errors and reserves the right to amend information without prior notice. This document does not create, specify, modify or replace any new or prior contractual obligations agreed upon in writing between Recticel Insulation and the user.

Recticel Insulation

Enterprise Way, Whittle Road, Meir Park, Stoke-on-Trent, Staffordshire, ST3 7UN, UK







Insulation Values		
Thickness (mm)	λ _D -value (W/mK)	R _D -value (m²K/W)
30	0.022	1.35
40	0.022	1.80
50	0.022	2.25
60	0.022	2.70
70	0.022	3.15
75	0.022	3.40
80	0.022	3.60
90	0.022	4.05
100	0.022	4.50
110	0.022	5.00
120	0.022	5.45
130	0.022	5.90
140	0.022	6.35
150	0.022	6.80
160	0.022	7.25

Other / Miscelaneous

Production Plant

Recticel Insulation Enterprise Way, Whittle Rd, Meir Park, Stoke-on-Trent, StaffordshireST3 7UN

Care has been taken to ensure that the content of this document is as accurate as possible. Please note that technical specifications may vary from country to country. Recticel Insulation does not accept any liability for clerical errors and reserves the right to amend information without prior notice. This document does not create, specify, modify or replace any new or prior contractual obligations agreed upon in writing between Recticel Insulation and the user.

Recticel Insulation

Enterprise Way, Whittle Road, Meir Park, Stoke-on-Trent, Staffordshire, ST3 7UN, UK



